

EAST Search History

EAST Search History (Prior Art)

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
S1	2	((("4143209")) or ("4859811")),PN.	USPAT	OR	OFF	2009/02/05 18:32
S2	1	"427".clas. and wire and (core near2 steel) and (coat\$3 near2 brass) and (draw\$3 near2 die)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 19:13
S3	72	"427".clas. and wire and core and coat\$3 and (draw\$3 near2 die)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 19:26
S4	8	S3 and plasma	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 19:26
S5	181	"428".clas. and wire and core and coat\$3 and (draw\$3 near2 die)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 19:39
S6	21	S5 and plasma	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 19:39
S7	3636	"427".clas. and (plasma with oxide)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:13
S8	681	"427".clas. and (plasma with oxide) and wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:13
S9	587	"427".clas. and (plasma with oxide) and wire and coat\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:13
S10	306	"427".clas. and (coat \$3 same(plasma with oxide)) and wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:14

S11	16	"427".clas. and (plasma with oxide with impurities) and wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:31
S12	395	"427".clas. and (oxide with impurities) and plasma and coating	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:43
S13	85	"427".clas. and (oxide with impurities) and plasma and coating and wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 20:43
S14	1955	(metal near2 wire) and coat\$3 and core and layer and (plasma or sputtering or (voltaic adj arc))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 21:19
S15	549	S14 and ((heat\$3 or thermal\$3) near2 treat\$4)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 21:20
S16	84	S15 and ((wire near2 draw\$3) or (draw\$3 near2 die))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/05 21:21
S17	6	("3055089" "4517066" "4725340" "4988552" "5219668" "5403419").FN.	USPAT	AND	ON	2009/02/06 13:57
S18	5	("3277564" "4143209" "4704337" "4859811" "5765418").FN.	USPAT	AND	ON	2009/02/06 13:58
S19	20	(electroplating with "plasma chemical vapor deposition")	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/02/06 16:07
S20	132	(ternary near3 alloy) near3 (coat or coating)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2009/10/22 15:57

S21	55	(ternary near3 alloy) near3 (coat or coating)	USPAT	AND	ON	2009/10/22 15:58
S22	1119	(electroplating with (plasma near2 deposition))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2010/08/28 22:41
S23	16	(electroplating with (plasma near2 deposition)) with wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2010/08/28 22:41
S24	281	(electroplating with (plasma near2 deposition)) and rubber	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2010/08/28 22:52
S25	243	(electroplating with (plasma near2 deposition)) and rubber and wire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2010/08/28 22:52
S26	19	(electroplating with (plasma near2 deposition)) and rubber and wire and tire	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	AND	ON	2010/08/28 22:53

EAST Search History (Interference)

< This search history is empty >

8/ 29/ 2010 11:54:03 AM**C:\Documents and Settings\dwolfe\My Documents\EAST\Workspaces\10537173****Method of Forming Coated Metal Wire.wsp**